CAST-A-SEAL® 402/402F

PRODUCT SPECIFICATION and SELECTION

Submittal Specification

A flexible Pipe-to-Structure connector shall be employed in the connection of the sanitary sewer pipe to precast structures. The connector shall be CAST-A-SEAL® 402/402F as manufactured by Press-Seal Gasket Corporation, Fort Wayne, Indiana, or approved equal. The connector shall be the sole element relied on to assure a flexible, watertight seal of the pipe to the precast structure. The connector shall consist of a rubber gasket and an external take-up clamp.

The rubber gasket element shall be constructed solely of synthetic or natural rubber, and shall meet or exceed the physical property requirements of ASTM C 923.

The external take-up clamp shall be constructed of Series 300 non-magnetic stainless steel and shall utilize no welds in its construction. The clamp shall be installed by torquing the adjusting screw using a torque-setting wrench available from the connector manufacturer.

Selection of the proper size connector for the structure and pipe requirement, and installation thereof, shall be in strict conformance with the recommendations of the connector manufacturer. Any dead end pipe stubs installed in connectors shall be restrained from movement per ASTM C 923.

The finished connection shall provide sealing to 13 psi (minimum) and shall accommodate deflection of the pipe to 7 degrees (minimum) without loss of seal.

Vacuum testing shall be conducted in strict conformance with ASTM C 1244 prior to backfill. Other testing shall be conducted in strict conformance with the requirements of the connector manufacturer.

CAST-A-SEAL 402	PIPE SIZE	PIPE O.D. RANGE	WALL THICKNESS*	APPLICATION
452.0250	1.25” - 2”	1.5” - 2.75”	2.5” - 6”	STANDARD
452.0450	4”	4.2” - 4.7”	2.5” - 6”	STANDARD
452.0402F1	4”	4.2” - 4.7”	2.5” - 3.5”	Closed Face
452.0650	6”	6.2” - 6.7”	2.5” - 6”	STANDARD
CAS ADAPTER	3”	3.2” - 3.6”	---	Use with 4” CAST-A-SEAL

PRODUCT PERFORMANCE

CAST-A-SEAL402/402F meets and/or exceeds all requirements of ASTM C 923, including physical properties of materials and performance testing, including:

- 13 psi minimum in straight alignment
- 10 psi at minimum 7°angle
- 10 psi minimum under shear load of 150 lbs/in. pipe diameter

CAST-A-SEAL 402/402F meets and/or exceeds the requirements of the following Standards, Specifications, Codes, and Test Methods:

- ASTM C 923 *Standard Specification for Resilient Connectors Between Reinforced Concrete Manhole Structures, Pipes, and Laterals*
- ASTM C 1644 *Standard Specification for Resilient Connectors Between Reinforced Concrete On-SIte Wastewater Tanks and Pipes*
- ASTM C 1478 *Standard Specification for Storm Drain Resilient Connectors Between Reinforced Concrete Storm Sewer Structures, Pipes and Laterals*
- ASTM C 1244 *Standard Test Method for Concrete Sewer Manholes by the Negative Air Pressure (Vacuum) Test*
- IAPMO/ANSI Z1000 *Standard for Prefabricated Septic Tanks*
- IAPMO/ANSI Z1001 *Standard for Prefabricated Gravity Grease Interceptors*
- *NPCA Best Practices Manual for Precast Concrete On-Site Wastewater Tanks*
- *NOWRA Model Code Framework*

TYPICAL TEST RESULTS for CAST-A-SEAL 402/402F (as in ASTM C 1644, C 923, and C 1478)			
Test	ASTM Test Method	Test Requirements	Typical Result
CHEMICAL RESISTANCE; 1N SULFURIC ACID and 1N HYDROCHLORIC ACID	D 534, AT 22ºC FOR 48 HRS	NO WEIGHT LOSS NO WEIGHT LOSS	NO WEIGHT LOSS NO WEIGHT LOSS
TENSILE STRENGTH	D 412	1200 PSI, MIN.	2100 PSI
ELONGATION AT BREAK	D 412	350%, MIN.	525%
HARDNESS	D 2240 (SHORE A DUROMETER)	±5 FROM THE MANUFACTURER’S SPECIFIED HARDNESS	<2
ACCELERATED OVEN-AGING	D 573, 70± 1ºC FOR 7 DAYS	DECREASE OF 15%, MAX. OF ORIGINAL TENSILE STRENGTH, DECREASE OF 20%, MAX. OF ELONGATION	-13% TENSILE CHANGE, -14% ELONGATION CHANGE
COMPRESSION TEST	D 395, METHOD B, AT 70ºC FOR 22 HRS	DECREASE OF 25%, MAX. OF ORIGINAL DEFLECTION	13%
WATER ABSORPTION	D 471 IMMERSE 0.75 BY 2-IN.SPECIMEN IN DISTILLED WATER AT 70ºC FOR 48 hrs	INCREASE OF 10%, MAX. OR ORIGINAL BY WEIGHT	3.50%
OZONE RESISTANCE	D 1171	RATING 0	PASS
LOW-TEMP, BRITTLE POINT	D 746	NO FRACTURE AT -40ºC	PASS
TEAR RESISTANCE	D 624, METHOD B	200 LBF/IN. (MIN.)	450 LBF/IN.

Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2010.

PRESS-SEAL GASKET CORPORATION
Protecting Our Planet’s Clean Water Supply
Press-Seal Gasket is an ISO 9001:2008 and ISO 14001:2004 Registered Company
800-348-7325 Fax (260) 436-1908
email: sales @press-seal.com
web: www.press-seal.com
Made in USA