



EZ-STIK #3

BUTYL SEALANT IN TROWELABLE FORM

Why It's Better

- Contains high-quality butyl rubber base
- Excellent gap-filling and crack-filling qualities
- An ideal repair/rehabilitation material
- Provides an adhesive and cohesive seal
- All-weather performance
- Good adhesion to dry concrete, commonly specified concrete coatings, steel, glass, or painted surfaces
- Remains permanently flexible
- Long service life
- Resists temperature extremes, and acids and alkalis

What It Is

TROWELABLE EZ-STIK #3 is a uniquely formulated butyl sealant suitable for pumping or trowel dispensing for concrete structures as a primary or secondary joint seal.

How It Performs

EZ-STIK #3 BUTYL JOINT SEALANT in TROWELABLE FORM

meets or exceeds all requirements of:

Federal Specification TT-S-001657
for Solvent Release Butyl Sealants.

Typical Applications

- Concrete Joint Repair
- Sanitary Manhole Joints
- Stormwater Manhole Joints
- Irrigation and Drainage Systems
- Box Culverts
- Elliptical/Arch Pipe
- Architectural Foundations
- Concrete Crack Repair
- Underground Utility Vaults
- Stormwater Treatment Structures
- Stormwater Inlet Structures
- On-Site Treatment Tanks
- Grease Interceptors
- Wet Wells

TROWELABLE EZ-STIK #3 is available in 5 gallon pails or in cartons of 12 - 11 ounce caulking tubes.

TYPICAL PROPERTIES

Coverage @ .25" Thick 7 sq. ft./gal.	Shelf Life One Year Minimum
Tack-Free Time Less Than 3 Hours: ASTM D-2377	Water Resistance Excellent. Will not lose adhesion when exposed to 100% relative humidity or water immersion over an extended period of time.
Cure Time Fully Cured Within 21 days at 77° ± 5°F	Acid Resistance Excellent. No visible sealant damage after 30 days of immersion in 20% sulfuric, hydrochloric or nitric acid.
Color Black	
Specific Gravity 1.17 ± .05	
Solids Content 75.0 ± 3%	
Boeing Sag 0.05" Maximum: ASTM D-2202	
Viscosity 55 ± 15 Seconds: ASTM D-2452	
Flash Point 52°F	

Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2010.

