# **EZ-STIK #3** BUTYL SEALANT IN TROWELABLE FORM



#### Where To Use

- Concrete joint repair
- Sanitary Manhole Joints
- Stormwater Manhole Joints
- Irrigation and Drainage Systems
- Box Culverts
- Elliptical/Arch Pipe
- Architectural Foundations
- Concrete crack repair
- Underground Utility Vaults
- Stormwater Treatment & Inlet Structures
- On-Site Treatment Tanks
- Grease Interceptors
- Wet Wells

# What It Is

EZ-Stik #3 is a trowelable butyl sealant suitable for pumping or trowel dispensing onto concrete structures. It can be used as a primary or secondary flexible seal that bonds to a wide variety of materials.

The physical properties of the sealant resists temperature extremes, acids and alkalis.

#### **How It Works**

- Clean and dry surface.
- Apply and smooth with a clean edge trowel blade at <sup>1</sup>/<sub>4</sub>" minimum thickness.
- If using in water collection system, do not backfill immediately.

### Why It's Better

- High-quality butyl rubber base.
- Excellent gap and crack filling properties.
- Resistance to acids and alkalis.
- All-weather protection.
- A permanent flexible solution.

#### Performance

EZ-Stik #3 Butyl Joint Sealant in trowelable form meets or exceeds all requirements of:

Federal Specification TT-S-001657



Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2022.

**Phone:** 800-348-7325 **Fax:** (260) 436-1908 PRESS-SEAL CORPORATION Protecting Our Planet's Clean Water Supply ISO 9001: Registered • Version 03.21.22.8.46

#### TYPICAL PROPERTIES

Coverage@ .25" Thick 7 sq. ft./gal.	Shelf Life One Year Minimum
Tack-Free Time Less Than 3 Hours: ASTM D-237	7 Water Resistance Excellent. Will not lose adhesion
Cure Time Fully Cured Within 21 days at	when exposed to 100% relative
77° ± 5°F	humidity or water immersion over
Color Black	an extended period of time.
Specific Gravity 1.17 ± .05	Acid Resistance Excellent. No visible sealant
Solids Content 75.0 ± 3%	damage after 30 days of
Boeing Sag 0.05" Maximum: ASTM D-2202	immersion in 20% sulfuric,
Viscosity 55 ± 15 Seconds: ASTM D-2452	hydrochloric or nitric acid.
Flash Point 52°F	

TROWELABLE EZ-STIK #3 is available in 5 gallon pails or in cartons of 12 - 11 ounce caulking tubes.

# Must ship via truck freight due to flammability.

Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2022.



PRESS-SEAL CORPORATION Protecting Our Planet's Clean Water Supply ISO 9001: Registered - Version 03.21.22.8.46

Email: sales @press-seal.com Web: www.press-seal.com

## **EZ-STIK #3** INSTALLATION INSTRUCTIONS

1. Clean and dry the concrete surface to which the #3 EZ-STIK will be applied. Remove any dirt and/ or mud adhering to the surface. The surface must be dry for the #3 EZ-STIK to adhere and bond to the concrete.

#4 EZ Primer can be applied to the surface to increase adhesion of the #3 EZ-STIK.

2. The #3 EZ-STIK should be applied with a smooth-edge trowel. The #3 EZ-STIK should be applied a minimum of 1/4" thick. The surface to be protected must be totally covered with no surface showing through the #3 EZ-STIK.

Coverage is 7 square feet per gallon when applied 1/4" thick.

- 3. When using #3 EZ-STIK as an external chimney seal (Butyl Rubber Backplaster), apply #3 EZ-STIK 6" from below the top cone to the casting. The #3 EZ-STIK trowelable should be applied 1/4" thick with a smooth-edge trowel. After coating the chimney, with the #3 EZ-STIK, wrap the applied #3 EZ-STIK with a 6mm polyethylene plastic sheeting by Visqueen or approved equal. Wait 20 minutes before backfilling.
- 4. The structure should not be backfilled for a minimum of 20 minutes after coating with the #3 EZ-STIK. This allows the solvents to dispense throughout the #3 EZ-STIK.

Should you need further information or have questions concerning theses installation instructions, please contact our Customer Service Department at 800-348-7325.



Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2022.

Phone: 800-348-7325 Fax: (260) 436-1908 PRESS-SEAL CORPORATION Protecting Our Planet's Clean Water Supply ISO 9001: Registered - Version 03.21.22.8.46

Email: sales @press-seal.com Web: www.press-seal.com