# **EZ-STIK**

### PREMIUM BUTYL JOINT SEALANT







# Where To Use

- Sanitary Manhole Joints
- Stormwater Manhole Joints
- Irrigation and Drainage Systems
- · Box Culverts
- · Elliptical/Arch Pipe
- Architectural Foundations
- Underground Utility Vaults
- · Stormwater Treatment & Inlet Structures
- · On-Site Treatment Tanks
- Grease Interceptors
- · Wet Wells

Store sealant and Wraps under cover. Once pallet wrapping is removed or damaged, weather can damage the packaging and the product.

### What It Is

The EZ-Stik butyl rubber all-weather joint sealant in rope form seals all forms of underground concrete and containment structures watertight.

Containing a higher percentage of butyl rubber, EZ-Stik provides a better performing joint sealant for longer service life.

EZ-Stik comes in many sizes and shapes for sealing both precision and non-precision joints in manhole, catch basins, curb inlets, vaults, pipe, box culverts, and other sanitary and drainage products.

## **How It Works**

- Sealant is applied as a continuous ring around entire joint.
- The excess sealant is then cut to length to create a butt joint.
- Ends of butt joint are kneaded together.
- Protective release paper is removed from the sealant ring.

# Why It's Better

- A variety of shapes and sizes to fit almost any application.
- Allows for joint movement and differential settlement in low temperature in accordance to ASTM C 765 - Standard Test Method for Low Temperature Flexibility of Preformed Tape Sealants.
- Tested to higher standards than bitumen (mastic) and blended materials including ASTM C990 Section 6.2 Butyl Rubber Sealants.
- Provides rebound for joint settlement and movement; meets ASTM C972 for compression recovery at 77°F
- and 32F.



Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2024.

113

# **EZ-STIK**SUBMITTAL SPECIFICATIONS

The joints and/or joint surfaces of the structures shall be sealed with a butyl rubber based preformed flexible sealant conforming to ASTM C990, paragraph 6.2, Butyl Rubber Sealant, ASTM C 765 Low Temperature and Flexibility, ASTM C 972-00 (2011): Butyl sealants provide rebound for joint settlement and movment and ASTM C 972 Compression Recovery; compression index at 32° F, Ibf/in³ 200 max.

The material shall be PRO-STIK or EZ-STIK as supplied by PRESS-SEAL CORPORATION, Fort Wayne, Indiana, or approved equal. The butyl material shall

consists of 50% (min.) butyl rubber and shall contain 2% or less volatile matter.

For preformed joint sealants, the sealant shall be sized such that the joint is filled to 50% (min.) of its annular volume when fully assembled, and the sealant shall have the ends kneaded together at the overlap. Primer and/or adhesive as recommended by the sealant supplier shall be employed for adverse, critical, or other applications.

Testing of joints and compliance with construction requirements shall be conducted in strict conformance with the requirements of the sealant supplier.

### **Product Performance**

EZ-STIK BUTYL JOINT SEALANT meets or exceeds all requirements of the following Standards, Specifications and/or Test Methods:


- ASTM C990 Standard Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants; Section 6.2 Butyl Rubber Sealants
- AASHTO M198 Joints for Circular Concrete Sewer and Culvert Pipe Using Flexible Watertight Gaskets
- ASTM C972 00(2011) Standard Test Method for Compression-Recovery of Tape Sealant
- ASTM C765 97(2015) Standard Test Method for Low-Temperature Flexibility of Preformed Tape Sealants



Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2024.

Web: www.press-seal.com

# **EZ-STIK SELECTION GUIDE**



Dimensions		Round	Roll Length		Rolls per	Cartons per	Dort No.
INCH	mm	Equivalent	FEET	Meter	Carton	Pallet	Part No.
.45" X .45"	11 X 11 MM	1/2"	21.75'	6.95 M	12	40	277.1
.675" X .675"	17 X 17 MM	3/4"	14.5'	4.64 M	8	40	277.2B
.89" X .89"	23 X 23 MM	1"	14.5'	4.64 M	6	40	277.3
1" X 1.255"	25 X 31 MM	1.25"	14.5'	4.64 M	4	40	277.4C
1.187" X 1.5"	30 X 38 MM	1.50"	10.5'	3.2 M	4	40	277.5
1.875" X 1.675"	48 X 43 MM	2"	7'	2.1 M	3	40	277.6A
3/8" round	9.5 MM	3/8"	15'	4.5 M	12	56	288.103
3.5" X 3/8"	90 X 10 MM	3.5" X 3/8"	16'	4.9 M	2	56	287.288A
3.5" X 5/8"	89 X 16 MM	3.5" X 5/8"	14.5'	4.64 M	2	40	287.329A
7/8" X 1-3/4"	22 X 44 MM	7/8" X 1.75"	14.5'	4.64 M	4	40	287.327
1/2" X 1-1/2"	13 X 38 MM	1/2" X 1.50"	21.75'	6.95 M	4	40	288.320
1/4" X 1/2"	6.3 X 13 MM	1/4" X 1/2"	20'	6.1 M	20	56	288.406

Custom Sizes Available Upon Request

#### Also Available in Trowelable Bulk and Easy to Pump Bulk

All sizes sold 40 cartons per pallet. All pallets are shrink wrapped for outside storage. Quantity discounts available - contact our Customer Service Department.

Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2024.

Phone: 800-348-7325 Fax: (260) 436-1908



EZ-STIK is a butyl rubber based sealant designed to be permanently flexible, tacky and resistant to moisture and deterioration by exposure to dilute chemical solutions. EZ-STIK meets ASTM C990, Section 6.2 requirements for Butyl Rubber Sealant, and AASHTO M198.

### **Typical Properties**

The following values represent typical properties of EZ-STIK

	Test Method	Requirement	EZ Stik
Butyl Rubber (Hydrocarbon Content)	ASTM D4	50% min.	54.80%
Ash Inert Mineral Filler %	AASHTO T111	30% min.	45.2%
Volatile Matter (AASHTO T47)	ASTM D6 / AASHTO T47	2% max.	0.90%
Specific Gravity @ 77°F (25°C)	ASTM D71 / AASHTO T229	1.15 - 1.50	1.39 g/mL
Ductility @ 77°F (25°C)	ASTM D113 / AASHTO T51	5.0 min.	9.5 cm
Flash Point C.O.C.	ASTM D92	350°F (177°C) min	528°F (276°C)
Fire Point C.O.C.	ASTM D92	375°F (191°C) min	538°F (281°C)
Compression @ 77°F (25°C)			80 lbs/in³
5 minute recovery	ASTM C972	100 max	6.1 mm
2 hour recovery			6.6 mm
Compression @ 32°F (0°C)			130 lbs/in³
5 minute recovery	ASTM C 972	200 max	6.4 mm
2 hour recovery			7.0 mm
Cone Penetration @ 77°F (25°C)	ASTM D217	50 to 120	72 dmm
Cone Penetration @ 32°F (0°C)	ASTIVI D217	30 min	41 dmm
Low Temp Flexibility	ASTM C765	180° bend, no cracking or loss of adhesion.	Pass
Adhesion after impact	ASTM C766	No greater loss than 50% adhesion.	Pass - 0% adhesion loss.
Chemical Resistance			
5% NaOH			
5% KOH		No deterioration, cracking, or swelling after separate 30	Pass
5% H2SO4			
5% HCI	ASTM C990		
5% Saturated H2S		day immersions at ambient conditions.	
5% Formaldehyde	]		
5% Formic Acid			

**Application Properties** 

Service Temperature Range -40°F to 250°F (-40° to 121° C) 20°F to 120°F (-7° to 49° C) Application Temperature Storage Temperature Under 120°F (49° C) Shelf Life 2 Years minimum

Press-Seal believes all information is accurate as of its publication date. Information, specifications, and prices are all subject to change without notice. Press-Seal is not responsible for any inadvertent errors. Copyright 2024.